

COLOUR-CAT

DATA SHEET DS Ref: CCP270115



Manufactured under a certified quality assured system

Acid-Catalysed PIGMENTED

GLOSS, SEMI-GLOSS, SATIN & FLAT

Product Description

E: sales@pylon.com.au

A range of low formaldehyde pigmented acid-catalysed coating for use on interior timber, veneer and MDF substrates. Colour-Cat has high opacity, high solids, smooth 'off the gun' finish and is an easy to use system. Use as a self-sealer or in conjunction with Colour-Cat Primer.

Principal Uses

- * Commercial & domestic furniture
- * Shop fitting & joinery
- * Built-in wardrobes
- * Kitchen doors
- * Internal doors

Features & Benefits

- * Low VOC, MIR & formaldehyde
- * Free of hydrocarbon solvents
- * High opacity / coverage
- * High solids
- * High heat, alcohol & water resistance
- * Good resistance to abrasion
- * Excellent flow & self-levelling
- * Smooth 'off the gun' finish
- * UV Additive available

Solid Content

White Base 67% Clear Base 55%



Theoretical Coverage

White Base 5-6m² @ 150 WFT

(wet film thickness)

Clear Base 4-5m² @ 150 WFT

(wet film thickness)



Packaging

Part A 4Lt 20Lt

Part B 1Lt 25Lt



Mixing Instructions

Use a flat blade stirrer & mix **Part A** before and after adding **Part B** hardener.

Mix by volume:- 10 Parts A to 1 Part B
Stir thoroughly and leave to stand for
10 minutes.

* Add appropriate thinner and re stir.

Hardener

Ace-Cat Hardener

100mls per 1Lt of Part A



Thinning

* Add between 10 – 40% refer to page 2

'Application System Guide'.

Fast Thinners C

Medium Thinners A

Slow Ace-Cat Thinners



Drying Times

Dust Free 20-30 mins
Touch Dry 40 - 60 mins
Sanding / Recoat 2 - 4 hrs
Full Cure 7 days

Tested at 25° C & 60% relative humidity

@ 150 micron WFT



Pot Life 24 – 36 hours



E: sales@pylon.com.au

W: www.pylon.com.au

COLOUR-CAT

DATA SHEET DS Ref: CCP270115

To CERTIFICATION CERTIFICATION

Manufactured under a certified quality assured system

Acid-Catalysed PIGMENTED

GLOSS, SEMI-GLOSS, SATIN & FLAT

Application System Guide

(based at 25° C and 60% humidity)

| | % Thinners | | Tip | Air Pressure | | |
|--------------|---------------|----------|-------------|--------------|----------|---------|
| | White | Clear | Size | | Pressure | |
| | Base | Base | 0.20 | Gun | Pot | Pump |
| | | | | | | |
| Suction Pot | 20 - 30% | 15 - 25% | 1.6 - 1.8mm | 30 - 45psi | N/A | N/A |
| | | | | | | |
| Gravity Pot | 20 - 30% | 15 - 25% | 1.2 - 1.6mm | 30 - 45psi | N/A | N/A |
| | | | | | | |
| Pressure Pot | 20 - 30% | 15 - 25% | 1.2 - 1.6mm | 30 - 45psi | 6-10psi | N/A |
| | | | | | | |
| Air Assisted | | | | | | 1000 - |
| Airless | 10 - 20% | 5 - 15% | 9 – 11 thou | N/A | N/A | 1500psi |
| | | | | | | · |
| Straight | | | | | | 1000 - |
| Airless | 10 - 20% | 5 - 15% | 9 – 11 thou | N/A | N/A | 1500psi |

Refer to Pylon technical team for your specific requirements

Equipment Cleaning

MEK or Thinners C

Surface Preparation

- 1) All surfaces must be clean, dry and free from dust, grease, dirt and all other contaminants before proceeding and throughout the entire coating process.
- 2) For raw substrates fill small defects, cracks and holes with a suitable putty; allow sufficient time to dry as per manufacturers specifications.
- 3) Sanding
- a. Undercoated Surfaces: 280 320 grit free-cut sandpaper.
- b. Melamine / White Board: Sand thoroughly with 240 then 400 grit free-cut sandpaper.
- c. Raw MDF: Sand with 150 then 220 grit free-cut sandpaper.

Application Guidance

- Apply a tack coat and allow to flash off for 3 5 minutes;
- Then apply two even wet coats in a cross-hatch method;
- For optimum results leave between 4-8 hours and re-coat.



E: sales@pvlon.com.au

COLOUR-CAT

DATA SHEET DS Ref: CCP270115

Sent Certification of the Control of

Acid-Catalysed PIGMENTED

GLOSS, SEMI-GLOSS, SATIN & FLAT

Manufactured under a certified quality assured system

Problem Solving

- Orange peel; reduce the air pressure and/or adjust thinning ratio.
- Solvent boil; apply lighter coats, allow a longer flash off time or use a slower thinner.

Refer to Pylon technical team for your specific requirements

Storage Instructions

Store in an approved dangerous goods cabinet or bunker in dry condition below 30° C.

Shelf life; Part A & B - 12 months unopened. **Opened products**; Part A & B - 6 months.

Warnings

Pylon Coatings advises that:

- you review, understand and follow this data sheet and the MSDS before use;
- it will only support a coating system that is exclusively Pylon products;
- the total dry film thickness should not exceed 200 microns;
- Colour-Cat should be tested on the selected substrate before proceeding;
- Colour-Cat is not recommended for any surface that will be submerged in water;
- · Colour-Cat is for selected internal surfaces;
- Colour-Cat should only be applied when temperatures are above 10° C and below 35° C;
- Colour-Cat may not cure properly whilst temperatures are below 10° C;
- Colour-Cat is a specialised industrial coating and should only be applied by experienced and competent tradespeople.

Condition of Use

All Pylon Coatings products are manufactured from high-grade raw materials to ISO 2008 quality assured system. We have no control over the conditions under which these products are stored, transported, handled or used, so customers are advised to test the product before adapting them to their own use. The information contained in this data sheet is based on data appraised in our own laboratory and from comprehensive market research. Pylon Coatings can only control the quality and formulation of our own products, and therefore have no responsibility over the quality or consistency of other company's products or substrates that the products are being applied on. Due to the possible variations between our controlled laboratory test conditions and techniques, differences in application and the range of substrates in today's market, Pylon Coatings supplies its products only on the condition that the consumer is satisfied with the performance of the product in meeting their requirements.